



## QUICK CHECK

- Interior/Exterior
- Turps Wash Up
- Roller, Brush or Spray
- Recoat – 24 hours

### GENERAL DESCRIPTION

A full gloss oil based enamel of premium quality, suitable for interior or exterior use where excellent durability, opacity, gloss retention and resistance to wear and weathering is required.

### USES

As a high quality full gloss finish coat for appropriately prepared interior or exterior surfaces, giving a hard wearing finish to timber, masonry, metal substrates and broad wall surfaces.

### COLOURS

Available in a range of bases which allow machine tinting to a wide range of popular colours along with a range of full strength pre-packaged colours.

Bases available are Accent, Clear, Dark, Green, Green Oxide, Mid Tone, Red, Red Oxide, Sand, Ultra Deep, Yellow Oxide and White. Milled Colours are Black, Geranium, Lime Green, Marigold, Mission Brown, Orange and Royal Blue.

Tinter, if added, should be vigorously and thoroughly stirred or shaken into the paint immediately upon addition. This is to ensure full colour development of the tinter addition.

### SIZES

Available in 500 ml, 1 litre, 2 litre, 4 litre and 10 litre (depending on colour selection).

### COVERAGE

Approximately 10-12 square metres per litre on suitably prepared surfaces.

### APPLICATION

Roller, brush or spray.

**PROVIDE ADEQUATE VENTILATION DURING USE.**

### DRYING TIMES

Touch Dry Time - 4 - 6 hours.

Recoat Dry Time - 24 hours.

Drying times refer to normal conditions (20°C, 50% humidity). Under cooler, humid or still conditions, longer drying times may be necessary.

**DO NOT USE IN TEMPERATURES BELOW 10°C OR ABOVE 25°C.**

### SHELF LIFE

12 Months.

### SPECIFICATION

GPC Approval - GPC-E-15/4 & 15/3.

### DANGEROUS GOODS CLASSIFICATION

### **Flammable**

Class 3 Flashpoint 32°C

UN1263 PG111 Hazchem 3[Y].

### SURFACE PREPARATION

When using more than one can of product to complete a job, mix the contents of all cans in a clear glass or tin container. To avoid skin contact, we recommend the use of disposable or rubber gloves. Stir thoroughly before and during application using a broad flat stirrer. Prior to commencing the whole job, test the colour on a scrap, off-cut or inconspicuous area. Allow to dry for 24 hours before re-coating.

**Previously Painted Surfaces:** Scrape off loose and flaking paint. Wash with Haymes Uni-Kleen Sugar Soap, diluted as recommended. Fill nail holes, cracks and imperfections, sand smooth and dust down. Sand gloss and semi gloss surfaces thoroughly and wipe clean. Coat all bare areas with the appropriate primers and/or undercoats.

**New Interior or Exterior Timber:** Fill imperfections with Haymes Unifill. Sand smooth and dust down. Apply one coat of Haymes Wood Primer White then one coat of Haymes General Purpose Undercoat allowing a minimum of 16 hours between coats. Tinted undercoats may be required to improve opacity.

**New Paperfaced Plasterboard:** Fill any imperfections with Haymes Unifill, sand smooth and dust down. Apply one coat of Haymes Paper Faced Plasterboard Sealer.

**Fibrous or Set Plaster:** Fill any imperfections with Haymes Unifill, sand smooth and dust down. Apply one coat of Haymes Sealer Binder.

**Bare Galvanised Iron:** Remove oil and grease by washing down with clean Haymes Mineral Turpentine. Apply one coat of Haymes Metal Primer or Haymes Etch Primer. Allow four hours to dry before recoating with one coat of Haymes General Purpose Undercoat. Leave 16 hours before finishing coats.

### FINISHING

Apply two even coats of Haymes High Gloss Enamel by roller, brush or spray. Where multiple coats are required, light sanding

between coats is recommended.

### **MAINTENANCE**

Protect the coating against abrasive contact for 7 days. In dusty areas, wash down periodically with a mild detergent solution to refresh and preserve the coating.

### **THINNING & CLEAN UP**

Apply unthinned where possible, but if necessary thin with Haymes Mineral Turpentine, approximately 50ml per litre. For spray application, use approximately 100ml of Haymes Mineral Turpentine as thinner per litre (10%). Clean equipment with Haymes Mineral Turpentine immediately after use. Used

cleanup rags may spontaneously ignite. To avoid ignition immerse in water or store in a sealable glass container.

### **PAINTING CONDITIONS**

Do not apply Haymes High Gloss Enamel if the temperature is below 10°C. While in hot weather, avoid painting in direct sunlight. Avoid applying externally in late afternoon in winter or in doubtful weather as frost, dew or rain is likely to impair gloss or durability of the coating. Use away from naked flames.

### **STORAGE**

Protect from extremes of temperature. Store between 5°C and 30°C.

## **PRECAUTIONS**

- **Safety Directions:** **KEEP OUT OF REACH OF CHILDREN - DO NOT SWALLOW.** Breathing the vapour is harmful and may cause lung irritation. Avoid contact with skin and eyes. Wear suitable, protective clothing, eye protection and impervious gloves when mixing and using. Handling and usage of this product must be carried out under well ventilation conditions that prevent inhalation of vapours, dust or mist. Use the appropriate breathing equipment (refer to Aust Stand. 1716) when ventilation is restricted. Keep containers closed when not in use. Eliminate any source of ignition (open fires, pilot lights, furnaces, spark producing switches etc.) as this product is flammable. **DO NOT SMOKE** Take precautionary measures against static discharges. Used clean up rags may spontaneously ignite. To avoid ignition immerse in water or store in a sealable glass container.
- **First Aid Instructions:** If affected by inhalation, remove to fresh air. If breathing difficulty persists or occurs later, consult a doctor. If swallowed, **DO NOT INDUCE VOMITING** drink plenty of water and seek medical advice. Contact a Doctor or Poisons Information Centre (Phone 131126). If skin contact occurs, remove contaminated clothing and wash skin thoroughly with soap and water. If irritation occurs seek prompt medical advice. Immerse contaminated clothing in water for 24 hours and do not use until laundered. In case of eye contact, hold eyes open and flood with running water for at least 15 minutes seek medical advice.
- **Leaks, Spills and Disposal:** In the case of volatile, flammable product, shut off all ignition sources. Contain or shut off leak if safe to do so. For large leaks or spills of volatile, flammable product use respiratory protection, protective apparel and footwear. Spills should be absorbed either with rags (small spill) or dry sand/earth (large spill). In the case of flammable product spillage, use spark free implements to place rags or absorbed material into a solvent resistant container. Cover with water for 24 hours before disposal. **DO NOT** pour left over product down the drain - retain it in a marked sealed container for future use or disposal through chemical waste collection programmes. Dried empty cans can be recycled and should be disposed of via council steel recycling facilities. Freecall 1800 807 568 for information relating to cleaning up after application or disposal of surplus product.
- **Fire:** Use foam and breathing apparatus. Avoid breathing products of combustion.

For best results, preparation is vitally important when repainting. Always ensure that the adhesion of old paint is sound before proceeding. Exterior enamels have a tendency to chalk over a period of time. Oil based enamels yellow with age, particularly in the absence of natural light. Rapid yellowing is possible in poorly ventilated areas if ammonia (from household chemicals and water based paints) is present.

**For further information or to place an order, call  
Service Express direct: Phone - 1800 033 431  
or email at - [www.haymespaint.com.au](http://www.haymespaint.com.au)**